


**Product Data Sheet - Organic Pigments for Plastics**
**Acrolite Fast Violet KDP**

Edition:01/01/2017

<b>Color Index Name</b>	: Pigment Violet 23	<b>Color Index No.</b>	: 51319
<b>Chemical Class</b>	: Dioxines	<b>CAS No.</b>	: 6358-30-1
<b>Product Code</b>	:	<b>EINECS No.</b>	: 228 - 767 - 9

**Salient Feature:** Very strong, brilliant violet with better texture having good light fastness and weathering fastness. Most suitable for all type of plastics .In combination with Phthalocyanine pigment, it is possible to navy blue shade economically..

**Application Profile** (  Major use /  Can be used)

**Plastics**

PVC <input checked="" type="checkbox"/>	PP <input checked="" type="checkbox"/>	PE <input checked="" type="checkbox"/>	EVA / Rubber <input checked="" type="checkbox"/>	PUFoams <input checked="" type="checkbox"/>
---	--	--	--	---

**Physical Properties**

Appearance	Powder	PH (10% slurry)	6.0 – 8.0
Bulk Volume (lit/kg)	2.0- 3.0	Heat stability (° C)	260°C
Moisture content (% max)	1.0 max	Density (gm/cm3)	1.5 – 1.6
Oil absorption (ml/100 gm)	45- 50		

**Fastness Properties**

Acid (5%)	5	Alkali (5%)	5
Water	5	Mineral Turpentine Oil	5
Xylene	4	Methyl Ethyl Ketone	4
White Spirit	5	Ethyl Acetate	4-5
Butanol	5	Butyl Acetate	5
Linseed Oil	5	Di-Octyl Phthalate	5

**Fastness to Light**

Full shade	7	Tint shade (1:10 TiO2)	6
------------	---	------------------------	---

\* Details of Testing method used and any other properties details require, please contact to our technical dept directly.

\* For other applications governed by regulation ( e.g. Heavy Metals , banned amines , PCB, suitability of food & packaging , Dioxine etc )which are not listed here , please contact to our technical dept directly

For Technical Enquiry please contact

**Pidilite Industries Limited,**  
 Compartment No. 43,Plot No 9,  
 Marol Co-Operative Industrial Estate Ltd,  
 Marol Sagbaug Road, Andheri (East)  
 Mumbai – 400 059.

**Technical Service Laboratory**  
 Telephone : 0091-22-2851 6910-11  
 Fax No : 0091-22-2851 1874  
 e-mail : pidilitepigment@pidilite.co.in

For Price, Sample and MSDS please contact

**Pidilite Industries Limited,**  
 Ramkrishna mandir road,  
 P.O.No. 17411,  
 Andheri (East), Mumbai 400 059

**Marketing Pigment Division**  
 Telephone : 0091-22-2835 7025/7000  
 Fax No : 0091-22-2835 7008  
 e-mail : jiten.pandya@pidilite.com

© Registered Trade Mark of Pidilite Industries Limited, India.

The information contained herein is based on data available at the time of preparation of this data sheet, which Pidilite Industries Limited believes to be reliable. However, no warranty expressed or implied regarding the accuracy of this data. Pidilite Industries Limited shall not be responsible for the use of this information, or any product, method or apparatus mentioned and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment and the health and safety of your employees and users of this material.